

Cust#: HARSPPR Company#: HARRY COOPER SUPPLY
 MTR#: TCNP/TCNP21331.pdf PO#: P1341745 SO#: LGCBK0
 Item: N44L00D01A Bundle: YU187978 Heatno: YU187978

Stock 2145342 08/01/2021



SSFIT 1/2XCLOSE SCH 40 304
 STAINLESS STEEL NIPPLE



TA CHEN STAINLESS PIPE CO., LTD.

Mill Test Report

TCNP21331

Commodity : STAINLESS STEEL PIPE NIPPLE Customer : TA CHEN INTERNATIONAL, INC. EN 10204-3.1
 BARREL NIPPLE
 Specification : ASTM A312/A312M-2018a Destination : LOS ANGELES NO. 125 HSIN-TIEN 2ND ST.,
 ASME SA312-2017 ASTM A733-2003 JENG-TEH, TAINAN, TAIWAN
 TEL:(06)2793254 FAX:(06)2701382
 COUNTRY ORIGIN:TAIWAN
 Grade : TP304/304L Customer O/N : L81127 Certificate No : TN0046012
 Delivery Condition: Factory O/N : QA02T1837 Date : 2019/3/28 INVOICE No : QA02TN0046

Item No.	Case No. (Crate No.)	Heat No.	Size	Quantity (Pcs)	Weight (Kgs)	Chemical Composition in %									
						C	Si	Mn	P	S	Ni	Cr	Mo	N	
01	005	YU184449	1/8" X 3/4" NPT	SCH40S TBE	300	0.035	1.000	2.000	0.045	0.030	8.00	18.00	-	-	
02	005	YU184449	1/8" X 2" NPT	SCH40S TBE	900	0.025	0.350	0.990	0.028	0.0010	8.050	18.290	-	0.049	
03	005	YU180815	1/8" X 2-1/2" NPT	SCH40S TBE	100	0.026	0.370	1.180	0.036	0.0110	8.080	18.170	-	0.034	
04	005	YU187978	1/2" X 1-1/8" NPT	SCH40S TBE	400	0.026	0.400	0.840	0.037	0.0030	8.010	18.110	-	0.039	
05	005	5A234	1/2" X 2" NPT	SCH40S TBE	300	0.023	0.300	1.410	0.033	0.0077	8.040	18.180	-	0.076	

Total 2000 Remarks

Item No.	Tensile Test (Gage Lth=50mm)				Hardness Test HRB	Bend Test	Dimension And Surface Condition	Melt Source
	0.2% Yield Strength PSI	1.0% Yield Strength PSI	Tensile Strength PSI	Elongation %				
	30000		75000	T25/L35				
01	41200	-	99900	46	80.00	OK	TAIWAN	
02	41200	-	99900	46	80.00	OK	TAIWAN	
03	40200	-	93100	54	82.00	OK	TAIWAN	
04	41500	-	90800	53	82.00	OK	TAIWAN	
05	42500	-	93700	50	85.00	OK	TAIWAN	

1. MERCURY FREE

We hereby certify the above statement to be true and correct every detail
 TA CHEN has established a QMS according to ISO 9001, which is certified by LRQA (cert. no.10068149)

Manager of Inspection Section/George Yang